

## Eaglecrete® 1233/1300

### JGB Eaglecrete® 1233

**Tube:** Black Conductive Natural Rubber  
Abrasion loss Value: According to DIN 53516 ≤ 60 mm<sup>3</sup>

**Cover:** NR/SBR Blend

**Reinforcement:** Spiral Textile

**Couplings:** Heavy Duty, Vic, NPT and Metric  
Mtl Hardness: Rockwell C Scale 60 +/- 2

**Temperature:** -40°F to 180°F

**Branding:** EAGLECRETE® 1233 PSI WP



Part #	ID	OD	Plies	WP	Burst	Weight
	in	in		psi	psi	lbs/ft
060-0242-1000	1 ½	2.20	4	1233	2465	1.07
060-0322-0800	2	2.76	4	1233	2465	1.43
060-0402-1000	2 ½	3.31	4	1233	2465	1.96
060-0482-1000	3	4.01	6	1233	2465	2.72
060-0562-1000	3 ½	4.64	6	1233	2465	3.51
060-0642-1000	4	5.12	6	1233	2465	3.96
060-0802-1000	5	6.10	6	1233	2465	4.90

### JGB Eaglecrete® 1300

**Tube:** Black Conductive Natural Rubber  
Abrasion loss Value: According to DIN 53516 ≤ 60 mm<sup>3</sup>

**Cover:** NR/SBR Blend

**Reinforcement:** Spiral Textile

**Couplings:** Heavy Duty, Vic, NPT and Metric  
Mtl Hardness: Rockwell C Scale 60 +/- 2

**Temperature:** -40°F to 180°F

**Branding:** EAGLECRETE® 1300 PSI WP



Part #	ID	OD	Plies	WP	Burst	Min Bend Radius	Weight
	in	in		psi	psi	in	lbs/ft
060-0322-1300	2	2.76	2	1300	2900	7.87	2.04
060-0402-1300	2 ½	3.46	4	1300	2600	9.44	3.01
060-0482-1300	3	4.02	4	1300	2600	10.82	3.67
060-4692-1300	4	5.12	4	1300	2600	13.78	5.69
060-4802-1300	5	6.10	4	1300	2600	16.73	6.47



Download the JGB® Mobile App



Click for directions:

**JGB® Headquarters**  
Liverpool, NY 13088  
(315) 451-2770

**Buffalo Branch**  
Cheektowaga, NY 14225  
(716) 684-8224

**Southeast Hub**  
Charlotte, NC 28273  
(704) 588-9920

**St. Louis Branch**  
St. Louis, MO 63123  
(704) 588-9920

**Williston Branch**  
Williston, ND 58801  
(701) 774-2195

**Houston Branch**  
Pasadena, TX 77503  
(281) 930-7777

Connect with us:



www.jgbhose.com